

Dow Corning® 20 Release Coating

FEATURES

- Easy to use
- Does not discolor molded parts
- Solvent dilutable
- In most cases, a single application provides release through numerous molding cycles

BENEFITS

- Provides heat stable, non-carbonizing, non-oily parting film
- Minimum build-up on molds and dies

COMPOSITION

- Polydimethylsiloxane and high molecular weight silicone resin in solvent

Release coating for plastics, adhesives, and elastomeric products

APPLICATIONS

- In fabricating plastic parts, provides durable parting film for epoxies, melamimes, methacrylates, phenolics, polyesters, and polyurethanes.
- Releases silicone glass laminates and tubes and parts made from silicone molding compounds.
- Provides release for wood forming operations, metal making, and rubber gaskets.

TYPICAL PROPERTIES

Specification Writers: These values are not intended for use in preparing specifications. Please contact your local Dow Corning sales office or your Global Dow Corning Connection before writing specifications on this product.

CTM*	Property	Unit	Value
0005	Color		Colorless/ light straw
0208	Active material content	% w/w	50
0001A	Specific gravity @ 77°F (25°C)	g/ml	0.93
0004	Viscosity	cst	11.0
0021A	Flash point - closed cup Solvent	°C	32 Stoddard and Xylene
	Suitable solvents		Aliphatic and aromatic hydrocarbons

CTM: Corporate Test Method, copies of CTMs are available on request.

DESCRIPTION

Dow Corning® 20 Release Coating provides a durable parting film which effectively releases plastics, adhesives, and other elastomeric products that are sometimes difficult to release from mold surfaces, even with other silicones.

Dow Corning 20 Release Coating with 80 parts isopropanol (99%) and 10 parts toluene, rather than the previously mentioned solvents. Whenever using solvents, always provide adequate ventilation and follow the precautions on the manufacturer's label.

HOW TO USE

Dilution

For easier application and finer control of the amount applied to mold surfaces, *Dow Corning* 20 Release Coating should be diluted to one part coating to 5-10 parts solvent. If wetting is a problem, blend 10 parts

To break in molds with porous surfaces, a more concentrated solution – equal parts solvent and *Dow Corning* 20 Release Coating – may be used. Once the mold has been broken in, a more dilute solution may be used.

Frequency of application and proper concentration for optimum release should be established by small-scale trial runs under actual operating conditions before use in operation.

After dilution, *Dow Corning 20 Release Coating* can be applied by spraying, brushing, or wiping. Mold surfaces should be cleaned prior to application. Best parting characteristics are obtained when this product is applied in a very thin film.

Avoid excess.

Thick films do not give good release and may even cause sticking. Difficult release may also result from uneven dispersion or failure to wet surfaces completely. This may be corrected by rubbing out the release material until a thin, dry film is obtained.

After application, allow the mold surface to dry until completely free of diluent. Because the solvents used to dilute *Dow Corning 20 Release Coating* may be flammable, special care must be taken when applying the dilution to hot surfaces.

Cure

Although not essential, a heat cure produces better release and increased durability of the parting film. Heating the molds for 5-10 minutes at 93-204°C (200 – 400°F) is suggested.

HANDLING PRECAUTIONS

Dow Corning 20 Release Coating is supplied in a flammable solvent. Avoid heat, sparks, and open flame. Always provide adequate ventilation.

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS

AVAILABLE FROM YOUR LOCAL DOW CORNING SALES REPRESENTATIVE.

USABLE LIFE AND STORAGE

When stored at or below 30°C (86°F) in the original unopened containers, this product has a usable life of 24 months from the date of production. This product is classed as a flammable, with a flash point of 32°C (89.6°F). Handle and store with appropriate precautions.

PACKAGING

This product is available in 37.4- and 374-lb (17- and 170-kg) containers, net weight.

Samples are available in 1-lb containers, net weight.

LIMITATIONS

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

Finishing Molded Parts

The silicone release film formed by *Dow Corning 20 Release Coating* may, in some cases, interfere with the painting and bonding of molded parts. If a finish coat or bonding is involved, the effect of a silicone release agent should be thoroughly tested before use.

Should painting or bonding of molded parts be an issue, *Dow Corning* offers release agents that are compatible with many organic coatings and adhesive systems. These alternative release products provide good release and offer the advantage that residual film transferred to the molded part can be removed from the molded part without requiring extraordinary cleaning procedures prior to painting or bonding. Information about these *Dow Corning* release materials is available upon request.

HEALTH AND ENVIRONMENTAL INFORMATION

To support customers in their product safety needs, *Dow Corning* has an extensive Product Stewardship organization and a team of Health, Environment and Regulatory Affairs specialists available in each area.

For further information, please consult your local *Dow Corning* representative.

WARRANTY INFORMATION – PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that *Dow Corning's* products are safe, effective, and fully satisfactory for the intended end use.

Dow Corning's sole warranty is that the product will meet the *Dow Corning* sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. *Dow Corning* specifically disclaims any other express or implied warranty of fitness for a particular purpose or merchantability. Unless *Dow Corning* provides you with a specific, duly signed endorsement of fitness for use, *Dow Corning* disclaims liability for any incidental or consequential damages. Suggestions of use shall not be taken as inducements to infringe any patent.