



ECCOBOND[®] 45 Clear / CATALYST 15 LV Clear

General Purpose, Adjustable Flexibility Epoxy Adhesive

Key Feature:	Benefit:
<ul style="list-style-type: none"> Low viscosity 	<ul style="list-style-type: none"> Ease of use
<ul style="list-style-type: none"> Adjustable flexibility 	<ul style="list-style-type: none"> Hardness can be adjusted by varying amount of CATALYST 15 LV Clear
<ul style="list-style-type: none"> General purpose 	<ul style="list-style-type: none"> Bonds well to metal, glass and plastic substrates

Product Description:

ECCOBOND 45 Clear / Catalyst 15 LV Clear is a clear, unfilled epoxy adhesive which, by varying the amount of catalyst used, can adjust the hardness from flexible to rigid. It has an easy mix ratio range and bonds well to a wide variety of substrates.

Applications:

ECCOBOND 45 Clear / Catalyst 15 LV Clear is designed as a general purpose, clear adhesive and is particularly useful when bonding dissimilar substrates such as metal to plastic.

Instructions For Use:

Thoroughly read the information concerning health and safety contained in this bulletin before using. Observe all precautionary statements that appear on the product label and/or contained in individual Material Safety Data Sheets (MSDS).

To ensure the long term performance of the bonded assembly, complete cleaning of the substrates should be performed to remove contamination such as oxide layers, dust, moisture, salt, and oils which can cause poor adhesion or corrosion in a bonded part. For information on proper substrate preparation, refer to the reprint "Good Adhesive Bonding Starts With Surface Preparation" available from Henkel Corporation.

Some separation of components is common during shipping or storage. For this reason, it is recommended that the contents of the shipping container be thoroughly mixed prior to use. Power mixing is preferred to ensure a homogeneous product.

Accurately weigh resin and hardener into a clean container in the recommended ratio. Weighing apparatus having an accuracy in proportion to the amounts being weighed should be used.

Blend components by hand, using a kneading motion, for 2-3 minutes. Scrape the bottom and sides of the mixing container frequently to produce a uniform mixture. If possible, power mix for an additional 2-3 minutes. Avoid high mixing speeds which could entrap excessive amounts of air or cause overheating of the mixture resulting in reduced working life.

Apply the adhesive to all surfaces to be bonded and join together. In most applications only contact pressure is required.

Properties of Material As Supplied:

Property	Test Method	Unit	ECCOBOND 45 Clear	CATALYST 15 LV Clear
Chemical Type			Epoxy	Amine
Appearance	Visual		Clear yellow	Clear yellow
Density	ASTM-D-792	g/cm ³	1.16	0.97
Brookfield Viscosity	ASTM-D-2393	Pa.s cP	13 13,000	11 11,000

Properties of Material As Mixed:

Property	Test Method	Unit	Value		
			Rigid	Semi-rigid	Flexible
Mix Ratio - Amount of Catalyst 15 LV Clear per 100 parts of ECCOBOND 45 Clear		By Weight	50	100	200
Working Life (100 g @ 25°C)	ERF 13-70	minutes	120	90	90
Density	ASTM-D-792	g/cm ³	1.09	1.06	1.02
Brookfield Viscosity	ASTM-D-2393	Pa.s cP	12 12,000	12 12,000	12 12,000

Cure Schedule:

Cure at any one of the recommended cure schedules. Alternate cure schedules may also be possible. Contact your Henkel Corporation Technical Representative for further information.

Temperature	Cure Time
°C	Time
25	16-24 hours
45	4-6 hours
65	2-4 hours
90	30-60 minutes

Properties of Material After Application:

Property	Test Method	Unit	Value		
			Rigid	Semi-rigid	Flexible
Hardness	ASTM-D-2240	Shore	75D	60D	60A
Tensile Lap Shear Strength Aluminum to Aluminum @ 25°C	ASTM-D-1002	mPa psi	17 2500	13 1900	4 600
Temperature Range of Use		°C	-40 to +90	-55 to +80	-55 to +65
Dielectric Strength	ASTM-D-149	kV/mm V/mil	14 350	14 350	14 350
Dielectric Constant @ 1 MHz	ASTM-D-150	-	3.4	3.3	3.3
Dissipation Factor @ 1 MHz	ASTM-D-150	-	0.03	0.08	0.07
Volume Resistivity @25°C	ASTM-D-257	Ohm-cm	>10 ¹⁴	>10 ¹⁴	>10 ¹⁴

Storage and Handling:

The shelf life of ECCOBOND 45 Clear / CATALYST 15 LV Clear is 12 months at 25°C. For best results, store in original, tightly covered containers. Storage in cool, clean and dry areas is recommended. Usable shelf life may vary depending on method of application and storage temperature.

Health and Safety:

The ECCOBOND 45 Clear, like most epoxy compounds possesses the ability to cause skin and eye irritation upon contact. Certain individuals may also develop an allergic reaction after exposure (skin contact, inhalation of vapors, etc.) which may manifest itself in a number of ways including skin rashes and an itching sensation. Handling this product at elevated temperatures may also generate vapors irritating to the respiratory system.

The CATALYST 15 LV Clear is classified as a corrosive material. Direct contact with unprotected eyes or skin can cause severe burns. Certain individuals may also develop an allergic skin or respiratory reaction after exposure (skin contact, skin absorption, inhalation of vapors, etc.). These reactions may manifest themselves

in a number of ways including skin rashes, itching sensation and breathing difficulties. Handling this product may also generate vapors irritating to the respiratory system.

Good industrial hygiene and safety practices should be followed when handling this product. Proper eye protection and appropriate chemical resistant clothing should be worn to minimize direct contact. Consult the Material Safety Data Sheet (MSDS) for detailed recommendations on the use of engineering controls and personal protective equipment.

This information is only a brief summary of the available safety and health data. Thoroughly review the MSDS for more complete information before using this product.

Attention Specification Writers:

The values contained herein are considered typical properties only and are not intended to be used as specification limits. For assistance in preparing specifications, please contact Henkel Corporation Quality Assurance for further details.

Medical Implantable Disclaimer

"In the event this product is intended by you for use in implantation in the human body, you are hereby advised that Henkel Corporation has not performed clinical testing of these materials for implantation in the human body nor has Henkel Corporation sought, nor received, approval from the FDA for the use of these material in implantation in the human body. It is YOUR responsibility, as a manufacturer of any such device, to ensure that all materials and processes relating to the manufacture of any medical device fully comply with all applicable federal, state and local laws, rules, regulations and requirements as well as any such laws, rules, regulations, directives or other orders of any foreign country where such product is sold. If you have not undertaken the necessary investigations to ensure compliance you are advised NOT TO USE this product in the manufacture of any device which is to be implanted in the human body. No representative of ours has any authority to change the foregoing provisions."

Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.**

The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Americas
+1.888.943.6535

Europe
+44.1442.278.000

Asia
+86.21.3898.4800



For the most direct access to local sales and technical support visit: www.henkel.com/electronics