



ECCOBOND E3503-1

August 2010

PRODUCT DESCRIPTION

ECCOBOND E3503-1 provides the following product characteristics:

Technology	Epoxy
Appearance	Off-white
Cure	Heat cure
Product Benefits	<ul style="list-style-type: none"> • Thermally conductive • One component • Low temperature cure • Long pot life • High performance thermal management adhesive • Excellent dispensing characteristics • Fine filler • Thin bondline • Low thermal resistance
Application	Assembly
Filler Weight, %	15 to 20
Operating Temperature	-45 to 125 °C
Typical Package Application	LED displays and Heat sensitive devices

ECCOBOND E3503-1 is optimised for SMT dispense and the manufacturing of high volume assemblies. It has high adhesion to the substrate finishes commonly used in microelectronics and will not adversely affect solder processes.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Viscosity @ 25 °C, mPa·s (cP)	50,000 to 70,000
Specific Gravity	1.2 to 1.25
Work Life:	
@ 25°C, days	7
Shelf Life:	
@ -25 to -18°C, months	6
@ 25°C, days	7
Hegman Fineness, micron	20

Flash Point - See MSDS

TYPICAL CURING PERFORMANCE

Cure Schedule

Convection:

30 minutes @ 100°C or
10 minutes @ 120°C or
5 minutes @ 150°C

IR Oven:

20 minutes @ 100°C or
3 minutes @ 120°C or
1 to 2 minutes @ 150°C

Stroke Cure:

6 to 12 seconds @ 160°C

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties:

Coefficient of Thermal Expansion, K ⁻¹	70×10 ⁻⁶
Glass Transition Temperature (T _g), °C	90 to 100
Thermal Conductivity, W/mk	0.8
Extractable Ionic Content, ppm:	
Chloride (Cl ⁻)	≤100
Sodium (Na ⁺)	≤10
Potassium (K ⁺)	≤10
Ammonia (NH ₄ ⁺)	≤75
Hardness, Shore A	≥75

TYPICAL PERFORMANCE OF CURED MATERIAL

Die Shear Strength:

1.27 x 1.27 mm Die, Kg ≥2.0

Tensile Lap Shear Strength, MPa

≥8

GENERAL INFORMATION

For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS).

THAWING:

1. Allow container to reach room temperature before use.
2. After removing from the freezer, set the syringes to stand vertically while thawing.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: -25 to -18 °C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.



Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{N/mm}^2 \times 145 = \text{psi}$
 $\text{MPa} \times 145 = \text{psi}$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.2