



# STYCAST 2072 A/B

## Convenient Mix Ratio, General Purpose, Epoxy Encapsulant

Key Feature:	Benefit:
<ul style="list-style-type: none"><li>Low viscosity</li></ul>	<ul style="list-style-type: none"><li>Ease of dispensing and use</li></ul>
<ul style="list-style-type: none"><li>Convenient mix ratio and non-abrasive filler</li></ul>	<ul style="list-style-type: none"><li>Ideal for meter mixing and automated dispensing</li></ul>
<ul style="list-style-type: none"><li>General purpose</li></ul>	<ul style="list-style-type: none"><li>Used in a wide variety of applications</li></ul>

### Product Description:

STYCAST 2072 A/B is a two component, filled, low viscosity, epoxy encapsulant. It features a convenient 2 to 1 mix ratio and contains a non-abrasive filler. STYCAST 2072 A/B has good electrical and mechanical properties.

### Applications:

STYCAST 2072 A/B was designed as a general purpose epoxy encapsulant for dispensing from automatic meter/mix equipment.

### Instructions For Use:

Thoroughly read the information concerning health and safety contained in this bulletin before using. Observe all precautionary statements that appear on the product label and/or contained in individual Material Safety Data Sheets (MSDS).

To ensure the long term performance of the potted or encapsulated electrical / electronic assembly, complete cleaning of components and substrates should be performed to remove contamination such as dust, moisture, salt, and oils which can cause electrical failure, poor adhesion or corrosion in an embedded part.

### Properties of Material As Supplied:

Property	Test Method	Unit	Value - Part A	Value - Part B
Chemical Type			Epoxy	Amine
Appearance	Visual		Black liquid	Black liquid
Density	TP-13	g/cm <sup>3</sup>	1.67	1.47
Brookfield Viscosity	TP-10 or TP-11	Pa.s cP	22.5 22,500	5.7 5,700

### Properties of Material As Mixed:

Property	Test Method	Unit	Value
Mix Ratio - Amount of Part B per 100 parts of Part A		By Weight By Volume	50 50
Working Life (100 g @ 25°C)	ERF 13-70	Minutes	90
Density	TP-13	g/cm <sup>3</sup>	1.60
Brookfield Viscosity	TP-10 or TP-11	Pa.s CP	8.0 8,000

Some filler settling is common during shipping and storage. For this reason, it is recommended that the contents of the shipping container be thoroughly mixed prior to use. Power mixing is preferred to ensure a homogeneous product.

Accurately weigh resin and hardener into a clean container in the recommended ratio. Weighing apparatus having an accuracy in proportion to the amounts being weighed should be used.

Blend components by hand, using a kneading motion, for 2-3 minutes. Scrape the bottom and sides of the mixing container frequently to produce a uniform mixture. If possible, power mix for an additional 2-3 minutes. Avoid high mixing speeds which could entrap excessive amounts of air or cause overheating of the mixture resulting in reduced working life.

To ensure a void-free embedment, vacuum deairing or degassing should be performed to remove any entrapped air introduced during the mixing operation. Pump-down or pull vacuum on the mixture to achieve an ultimate vacuum or absolute pressure of 1- 5 torr or mm Hg. The foam will rise several times the liquid height and then subside. Continue vacuum deairing until most of the bubbling has ceased. This usually requires 3-10 minutes.

To facilitate deairing in difficult to deair materials, add 1-3 drops of an air release agent, such as ANTIFOAM 88, into 100 grams of mixture. Gentle warming will also help, but working life will be shortened.

Pour mixture into cavity or mold. Gentle warming of the mold or assembly reduces the viscosity. This improves the flow of the material into the unit having intricate shapes or tightly packed coils or components. Further vacuum deairing in the mold may be required for critical applications.

**Cure Schedule:**

Cure at any one of the recommended cure schedules. For optimum performance, follow the initial cure with a post cure of 2 - 4 hours at the highest expected use temperature.

Temperature	Cure Time
°C	Time (hour)
25	24 – 48
45	8 – 16
65	2 - 4

**Properties of Material After Application:**

Property	Test Method	Unit	Value
Hardness	TP-311	Shore D	89
Flexural Strength	ASTM-D-790	mPa psi	83 12,000
Coefficient of Thermal Expansion	TMA	10 <sup>-6</sup> /°C	61
Thermal Conductivity	ASTM-D-2214	W/m.K Btu-in/hr-ft <sup>2</sup> -°F	0.42 2.9
Temperature Range of Use		°C	-40 to +130
Dielectric Strength	TP-297	kV/mm V/mil	15.7 400
Dielectric Constant @ 1 mHz	TP-184	-	4.2
Dissipation Factor @ 1 mHz	TP-184	-	0.01
Volume Resistivity @ 25°C	TP-183	Ohm-cm	>10 <sup>14</sup>

*TPs are internal test procedures typically derived from ASTM or other norms. Copies of these test procedures can be obtained upon request.*

**Storage and Handling:**

The shelf life of STYCAST 2072 Parts A and B are 12 months at 25°C. For best results, store in original, tightly covered containers. Storage in cool, clean and dry areas is recommended. Certain resins and hardeners are prone to crystallization. If crystallization does occur, warm the contents of the shipping container to 50-60°C until all crystals have dissolved. Be sure the shipping container is loosely covered during the warming stage to prevent any pressure build-up. Allow contents to cool to room temperature before continuing.

**Health and Safety:**

The STYCAST 2072 Part A/B like most epoxy compounds, possesses the ability to cause skin and eye irritation upon contact. Certain individuals may also develop an allergic reaction after exposure (skin contact, inhalation of vapors, etc.) which may manifest itself in a number of ways including skin rashes and an itching sensation. Handling this product at elevated temperatures

may also generate vapors irritating to the respiratory system

Good industrial hygiene and safety practices must be used when handling this product. Proper eye protection and appropriate chemical resistant clothing must be worn to prevent contact. Consult the Material Safety Data Sheet (MSDS) for detailed recommendations on the use of engineering controls, personal protective equipment and first aid procedures.

*This information is only a brief summary of the available safety and health data. Thoroughly review the MSDS for more complete information before using this product.*

**Attention Specification Writers:**

The values contained herein are considered typical properties only and are not intended to be used as specification limits.

Medical Implantable Disclaimer

\*In the event this product is intended by you for use in implantation in the human body, you are hereby advised that Henkel Corporation has not performed clinical testing of these materials for implantation in the human body nor has Henkel Corporation sought, nor received, approval from the FDA for the use of these material in implantation in the human body. It is YOUR responsibility, as a manufacturer of any such device, to ensure that all materials and processes relating to the manufacture of any medical device fully comply with all applicable federal, state and local laws, rules, regulations and requirements as well as any such laws, rules, regulations, directives or other orders of any foreign country where such product is sold. If you have not undertaken the necessary investigations to ensure compliance you are advised NOT TO USE this product in the manufacture of any device which is to be implanted in the human body. No representative of ours has any authority to change the foregoing provisions.\*

**Note**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

**Trademark usage**

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

---

Americas  
+1.888.943.6535

Europe  
+44.1442.278.000

Asia  
+86.21.3898.4800



**For the most direct access to local sales and technical support visit: [www.henkel.com/electronics](http://www.henkel.com/electronics)**