



# LOCTITE<sup>®</sup> Big Foot<sup>™</sup> Acrylic Primer

October 2008

## PRODUCT DESCRIPTION

LOCTITE<sup>®</sup> Big Foot<sup>™</sup> Acrylic Primer provides the following product characteristics:

<b>Technology</b>	Acrylic
<b>Appearance</b>	Clear
<b>Cure</b>	Room temperature cure
<b>Application</b>	Non-slip coating
<b>Specific Benefit</b>	<ul style="list-style-type: none"> <li>Increases adhesion and coverage of Loctite<sup>®</sup> Big Foot<sup>™</sup> Acrylic Pedestrian Grade</li> </ul>

LOCTITE<sup>®</sup> Big Foot<sup>™</sup> Acrylic Primer is a single-component, zero V.O.C., water based acrylic primer designed for use with Loctite<sup>®</sup> Big Foot<sup>™</sup> Acrylic Pedestrian Grade Coating. It is designed to be used as a base coat for Loctite<sup>®</sup> Big Foot<sup>™</sup> Acrylic Pedestrian Grade on porous surfaces, wood and concrete. For metal surfaces use Loctite<sup>®</sup> Big Foot<sup>™</sup> Metal Primer. This product is typically used in applications with an operating range of -29 °C to +60 °C.

## TYPICAL PROPERTIES OF UNCURED MATERIAL

Viscosity @ 25°C, mPa·s (cP)	80 to 120 <sup>LMS</sup>
Volume of Solids, %	23
VOC, ASTM D 3960, g/l	0
Coverage	23.2 m <sup>2</sup> per 3.78 l
Weight Per Gallon, lbs/gal	8.5 to 8.7 <sup>LMS</sup>

## TYPICAL CURING PERFORMANCE

### Curing Properties

Drying Time @ 25 °C, hours	1 to 2
----------------------------	--------

## GENERAL INFORMATION

**This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials**

**For safe handling information on this product, consult the Material Safety Data Sheet (MSDS).**

### Directions for use:

#### Surface Preparation:

LOCTITE<sup>®</sup> Big Foot<sup>™</sup> Acrylic Primer can be applied to any clean, dry surface. Recommended methods of cleaning are as follows:

1. All surfaces to be coated should be sound, clean, dry and free of all contaminants.

2. Loose dirt and dust are best removed by a stiff bristle brush or by blowing down with dry, oil-free compressed air.

3. Oil, wax and grease should be removed by dissolving in a water-based cleaner/degreaser such as Loctite<sup>®</sup> Natural Blue Cleaner and Degreaser. Rinse thoroughly with fresh water while the dissolved solution is still wet. An alternate method is to clean with appropriate solvents such as mineral spirits or xylene as per SSPC-SP-1. It is important that the solvent be removed from the surface while still liquid and not be allowed to evaporate during the cleaning process and redeposit oil or grease on the deck. Ample solvent should be applied to the surface to completely dissolve the grease and oil. The solvent containing the dissolved grease and oil should be wiped up with clean rags before the solvent dries.

4. Depending on concentration and type, chemical contamination should be removed by detergent power washing followed by a liberal fresh water while the detergent is still wet. Allow surface to completely dry.

5. After cleaning, any remaining loose particles should be removed by brushing or blowing with dry, oil-free compressed air.

### New Concrete:

1. New concrete should be wet cured for at least three days and allowed to dry with good ventilation for an additional thirty days.

2. After proper curing, new floors must be swept clean and all contaminants which might interfere with the adhesion of the coating system including laitance, curing membranes, surface hardeners, greases and oils be removed.

3. An appropriate profile must be created using chemical or mechanical means.

4. The preferred method to prepare floor surfaces and to remove paint, laitance, curing membranes and surface hardeners is by mechanical removal of the same with a portable shot blast cleaning machine.

5. Chemical cleaning of laitance and unbounded particles can be accomplished by etching the surface with a muriatic acid or buffered acid solution. Follow acid manufacturer's application and safety instructions. After the acid has finished reacting with the concrete, the residue should be removed by a liberal fresh water rinse or preferably by power washing. Allow the surface to completely dry.

6. NOTE: Acid etching will not remove oil, grease or wax. If the acid does not bubble or foam when spread on the concrete, the surface should be examined for films or oil, grease, wax, curing membranes, hardeners or other sealers. If such film is present, it must be removed.

#### Aged and Uncoated Concrete Floors:

1. Proceed as for **New Concrete** with particular emphasis on examinations for grease, oil and chemical contamination and subsequent adequate cleaning.

#### Asphalt:

1. Sweep to remove all dirt and other loose contaminants. Remove oil, grease, dirt, etc., by dissolving in a water-based cleaner/degreaser such as Loctite® Natural Blue Cleaner and Degreaser then flush thoroughly with clean water and allow to dry.

#### Wood:

1. Remove any weathered wood to expose clean, sound wood. Smooth wood should be sanded to roughen up the surface.

#### Tile and Fiberglass:

1. Glazed or ceramic tile and glazed fiberglass must be sanded to remove all glaze and to roughen up the surface. Remove any residual sanding dust by air blowing or wiping with alcohol.

#### Application Method:

LOCTITE® Big Foot™ Acrylic Primer is a one-part compound. Stir thoroughly (approximately 1 to 2 minutes) with a mechanical mixer, Loctite® Big Foot™ Mixer Blades. Apply by using:

1. Roller Application - Use the bristle roller, Loctite® Big Foot™ Bristle Roller Cores. Apply uniformly.
2. Brush Application - Use a 10cm wide thin stock brush.
3. Spray Application - Airless, air assisted or conventional paint spray equipment can be used.
4. Loctite® Big Foot™ Acrylic Pedestrian Grade can be successfully applied to a primed surface after 1 to 2 hours @ 21°C.
5. Clean tools immediately after completing installation using soap and water.

**NOTE:** After 72 hours, the primed surface must be mechanically abraded or grit-blasted and LOCTITE® Big Foot™ Acrylic Primer reapplied.

#### Loctite Material Specification<sup>LMS</sup>

LMS dated April 04, 2002. Test reports for each batch are available for the indicated properties. LMS test reports include selected QC test parameters considered appropriate to specifications for customer use. Additionally, comprehensive controls are in place to assure product quality and consistency. Special customer specification requirements may be coordinated through Henkel Quality.

#### Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

**Optimal Storage: 8 °C to 21 °C. Storage below 8 °C or greater than 28 °C can adversely affect product properties.**

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

#### Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$   
 $\text{kV/mm} \times 25.4 = \text{V/mil}$   
 $\text{mm} / 25.4 = \text{inches}$   
 $\mu\text{m} / 25.4 = \text{mil}$   
 $\text{N} \times 0.225 = \text{lb}$   
 $\text{N/mm} \times 5.71 = \text{lb/in}$   
 $\text{N/mm}^2 \times 145 = \text{psi}$   
 $\text{MPa} \times 145 = \text{psi}$   
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$   
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$   
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$   
 $\text{mPa}\cdot\text{s} = \text{cP}$

#### Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

**Trademark usage**

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.3