



# Technical Process Bulletin

This Revision: 09/12/2008

## **TURCO 4338-L**

TURCO 4338-L is a 2-part liquid alkaline permanganate formulation developed specifically for jet engine cleaning

### **DESCRIPTION:**

TURCO 4338-L is a 2-part liquid alkaline permanganate formulation developed specifically for jet engine cleaning. TURCO 4338-L modifies high temperature heat scale by chemically changing the structure of the oxide deposit to one that is properly conditioned for ease of chemical removal in subsequent processing steps.

### **FEATURES:**

TURCO 4338-L offers these features:

Approved by Rolls-Royce, GEAE, and Pratt & Whitney. Supplied as two liquid concentrates that are mixed together with water for greater safety and ease of handling compared to powdered products. Each part may be used for both tank make-up and tank maintenance.

May be used over a wide range of concentrations to handle various types of scale.

TURCO 4338-L is used on all ferrous and high temperature alloys Turco 4338-L can be used in mild steel tanks

**NOTE:** TURCO 4338-L should not be used on reactive alloys such as aluminum.

### **HOW TO USE TURCO 4338-L:**

A. Prepare a solution of TURCO 4338-L by first adding enough water to comprise about 40% of the final volume. While mixing, add sufficient TURCO 4338-L Part 1 and TURCO 4338-L Part 2 for each individually to comprise 15 to 25% by volume of the final solution. TURCO 4338-L Parts 1 and 2 should be used in equal volumes. TURCO 4338-L Part 1 should be added to the water first, while mixing. The appropriate amount of TURCO 4338-L Part 2 should then be added to that solution, while continuing to mix. Heat to 90°C while mixing. Add sufficient good quality water to make up the final volume while mixing.

Step 1. Immerse parts in TURCO 4181-GL at 25-35% by volume at 80° to 95°C for 30 to 60 minutes.

Step 2. Thorough water overflow dip rinse.

Step 3. Immerse parts in TURCO 4338-L solution at 80° to 95°C for 30 to 60 minutes.

- Step 4. Thorough water overflow dip rinse.
- Step 5. Immerse in Scale Gon #7 at 20-30% by volume at 80° to 90°C for 30-60 minutes.
- Step 6. Water dip rinse. Follow with pressure rinse with air/water hand rinse gun to blast off the loosened scale deposit and reveal the shiny base metal surface.
- Step 7. Final clean in 4181-GL at 25-35% at 80° to 95°C.
- Step 8. Thorough water overflow dip rinse.

**CONTROL:****CONCENTRATION OF TURCO 4338L PART 1****Apparatus:**

1. 168522 - Pipet, measuring, 5ml
2. 164014 - Buret, 25 mL
3. 168497 - Beaker, 250 mL
4. 168509 - Cylinder, 50 mL
5. pH meter

**Reagents:**

1. 1.0 N Sulfuric Acid

**Procedure:**

1. Obtain a sample from the bath, cool to room temperature.
2. Pipet 5 mL into a 250mL beaker containing 100 mL DI water.
3. Titrate with 1.0 N sulfuric acid to pH 8.3 and record this value as 'A'. Continue titrating to pH 4.0 and record this value as 'B'

**Calculation:**

$$[(2 \times A) - B] \times 1.05 = \% \text{ by volume Turco 4338L Part 1}$$

**CONCENTRATION OF TURCO 4338L PART 2****Apparatus:**

1. 168522 - Pipet, 5 ml, measuring
2. 168517 - Pipet, 10 mL, volumetric
2. 164014 - Buret, 25 mL
3. 168513 - Erlenmeyer Flask, 250 mL
4. - Flask, Volumetric, 100 mL

**Reagents:**

1. 596015 - Titrating Solution 1565 (0.1N Ferrous Ammonium Sulfate)
2. 592431 - Titrating Solution 30 (0.1N Potassium Dichromate)
3. 592403 - Indicator 12 (Ferroun Indicator)
4. Concentrated Sulfuric Acid

**Procedure:**

1. Obtain a sample from the bath. Filter sample while warm (~120 F) through Whatman GF/A glass fiber filter paper or equivalent. Cool the filtered sample to room temperature.
2. Using a 5 mL measuring Pipet, measure 5 mL into a 100 mL volumetric flask. Make to volume with deionized water and mix.
3. Pipet a 10 mL aliquot into a 250 mL Erlenmeyer flask. Add 25 mL of deionized water and slowly add 2 mL of concentrated sulfuric acid.
4. Titrate with Titrating Solution 1565 to a pale yellow or yellowish-brown endpoint.

**Calculation:**

$$= \frac{\text{mL Titrating Solution 1565} \times \text{Normality of Titrating Solution 1565} \times 21.8}{\% \text{ by volume of Turco 4338-L Part 2}}$$

**Ferrous Ammonium Sulfate Standardization:**

1. Pipet 25 mL of 0.1N Ferrous Ammonium Sulfate into a 250 mL Erlenmeyer flask
2. Add 5 mL of concentrated sulfuric acid.
3. Add 4-6 drops of Indicator 12 (Ferrouin indicator)
4. Titrate with Titrating Solution 30 (0.1N Potassium Dichromate) to a bluish-green endpoint

**Calculation:**

$$\frac{(\text{mL } 0.1\text{N Potassium Dichromate}) \times (0.100)}{25} = \text{Normality of Ferrous Ammonium Sulfate}$$

**DISPOSAL INFORMATION:**

Dispose of sludge and/or spent solution per local, state and regional regulations. Refer to your HENKEL SURFACE TECHNOLOGIES MATERIAL SAFETY DATA SHEET for additional information.

**DANGER! Contact may cause severe burns to skin and eyes.**

The TURCO 4338-L solution contains sodium hydroxide and permanganate. Avoid contact with eyes, skin and clothing. Do not take internally. Use with adequate (equivalent to outdoor) ventilation.

TURCO 4338-L is a strongly alkaline, highly oxidizing solution which will produce burns on contact with skin. Protective clothing, such as a chemical face shield or goggles, gloves, boots and apron, made of alkali resistant materials should be worn when using

and handling this product.

Hazardous carbon monoxide gas can be formed upon contact with food and beverage products in enclosed spaces and can be fatal. Follow appropriate tank entry procedure. (See ANSI-Z117.1-1977.)

Store and transport in closed containers away from organic materials, such as paints, lubricants, paper and wood products, at a temperature below 55°C.

Before using this product refer to container label and HENKEL SURFACE TECHNOLOGIES MATERIAL SAFETY DATA SHEET for additional precautionary, handling and first aid information.

**NOTICE:**

The above information and recommendations concerning this product are based upon our laboratory tests and field use experience with this or similar products. However, since conditions of actual use are beyond our control, any recommendations or suggestions are made without warranty, express or implied. Manufacturer's and seller's sole obligation shall be to replace that portion of the product shown to be defective. Neither shall be liable for any loss, damage or injury, direct or consequential, arising out of the use of this product.

Rev. 8/00 (Sup. 8/99)

Henkel Technologies  
32100 Stephenson Highway  
Madison Heights, MI 48071  
Telephone: 248-583-9300  
Fax: 248-583-2976

"The information presented herein is our interpretation of certain test results and field experience to date. This information is not to be taken as warranty or representation for which we assume legal responsibility, nor as permission or recommendation to practice any patented invention without a license. It is offered solely for your consideration, investigation and verification." © Henkel Corporation.

**Form Revised 04 June 2001**