

HumiSeal 1B51™ Synthetic Rubber Conformal Coating Technical Data Sheet

HumiSeal 1B51™ is a fast drying, single component, synthetic rubber conformal coating that provides excellent moisture and environmental protection for printed circuit assemblies. Because of its unique base polymer, HumiSeal 1B51™ has extremely low moisture vapour permeability. The coating demonstrates excellent flexibility, low stress on components and is easily repaired. HumiSeal 1B51™ is in full compliance with the RoHS Directive 2002/95/EC.

Properties of HumiSeal 1B51™

Density, g/cm ³ per ASTM, Meth. D1475	0.89 ± .01
Solids Content, % by weight per Fed-Std-141, Meth. 4044	22 ± 1.5
Viscosity, centipoise per Fed-Std-141, Meth. 4287	185 ± 30
VOC, grams/litre	708
Drying Time to Handle per Fed-Std-141, Meth. 4061	10 minutes
Recommended Coating Thickness, microns	25 - 75
Recommended Curing Conditions	24 hrs @ RT or 30 min @ 76°C
Time Required to Reach Optimum Properties	7 days
Recommended Thinner (dipping & brushing)	HumiSeal Thinner 535
Recommended Thinner (spraying)	HumiSeal Thinner 521
Recommended Stripper	HumiSeal Stripper 1081
Shelf Life at Room Temperature, DOM	18 months
Thermal Shock, 50 cycles per MIL-I-46058C	-65°C to 125°C
Coefficient of Thermal Expansion - TMA	55 ppm/°C
Glass Transition Temperature - DSC	14°C
Modulus - DMA	93.1 MPa @ -20°C 73.5 MPa @ 0°C 35.3 MPa @ 20°C
Flammability, per UL 94	HB
Moisture Vapor Transmission, per JIS Z0208	15 g/m ² · day
Dielectric Withstand Voltage, volts per MIL-I-46058C	>1,500
Dielectric Breakdown Voltage, volts per ASTM, Meth. D149	4900
Dielectric Constant, at 1MHz and 25°C per ASTM-D150-65T	2.5
Dissipation Factor, at 1MHz and 25°C per ASTM-D150-65T	0.07
Insulation Resistance, ohms per MIL-I-46058C	200 x 10 ¹² (200T)
Moisture Insulation Resistance, ohms per MIL-I-46058C	10 x 10 ⁹ (10G)
Fungus Resistance, per ASTM-G21	Passes

Application of HumiSeal 1B51™

Cleanliness of the substrate is of extreme importance for the successful application of a conformal coating. Surfaces must be free of moisture, dirt, wax, grease, flux residues and all other contaminants. Contamination under the coating could cause problems that may lead to assembly failures.

Dipping

Depending on the complexity, density and configuration of components on the assembly, it may be necessary to reduce the viscosity of HumiSeal 1B51™ with HumiSeal Thinner 535 in order to obtain a uniform film. Once optimum viscosity is determined, a controlled rate of immersion and withdrawal (5-15 cm/min) will further ensure even deposition of the coating and a uniform film. During the application, evaporation of solvent causes an increase in viscosity that should be adjusted by adding small amounts of HumiSeal Thinner 535. Viscosity in the dip tank should be checked regularly, using a simple measuring device such as a Zahn or Ford viscosity cup.

HumiSeal 1B51™ Technical Data Sheet

Spraying

HumiSeal 1B51™ can be sprayed using conventional spraying equipment. Spraying should be done in an environment with adequate ventilation so that the vapour and mist are carried away from the operator. The addition of HumiSeal Thinner 521 is necessary to ensure a uniform spray pattern resulting in pinhole-free film. The amount of thinner and spray pressure will depend on the specific type of spray equipment used and operator technique. The recommended ratio of HumiSeal 1B51™ to HumiSeal Thinner 521 is 1:1 by volume, however the quantities may need to be adjusted to obtain a uniform coating.

Brushing

HumiSeal 1B51™ may be brushed with a small addition of HumiSeal Thinner 535. Uniformity of the film depends on component density and operator's technique.

Storage

HumiSeal 1B51™ should be stored away from excessive heat or cold, in tightly closed containers. HumiSeal products may be stored at temperatures of 0 to 35°C. Prior to use, allow the product to equilibrate for 24 hours at a room temperature of 18 to 32°C.

Caution

The solvents in HumiSeal 1B51™ are flammable. Material should not be used in presence of open flame or sparks. Use only in well-ventilated areas to avoid inhalation of vapours or spray. Avoid contact with skin and eyes. Consult MSDS prior to use.

Contact HumiSeal

HumiSeal North America

201 Zeta Drive
Pittsburgh, PA 15238
USA
Tel: +1 412-828-1500
Toll Free (US only): 866-828-5470
sales@humiseal.com

HumiSeal Technical Center

295 University Avenue
Westwood, MA 02090
USA
Tel: +1 781-332-0734
Fax: +1 781-332-0703
techsupport@humiseal.com

HumiSeal Europe

Albany Park, Frimley Road
Camberley, Surrey GU16 7PH
UK
Tel: +44 (0)1276 691100
Fax: +44 (0)1276 691227
europesales@chasecorp.com

HumiSeal Europe Support

Tel: +44 (0)1276 691100
Fax: +44 (0)1276 691227
europetechsupport@chasecorp.com

HumiSeal S.A.R.L

4/6 Avenue Eiffel
78420 Carrieres-Sur-Seine
France
Tel: +33 (0) 1 30 09 86 86
Fax: +33 (0) 1 30 09 86 87
humiseal.sarl@chasecorp.com

HumiSeal Asian Support

Tel: 852-9451-6434
Fax: 852-2413-6289
asiatechsupport@humiseal.com

The information contained here is provided for product selection purposes only and is not to be considered specification or performance data. Under no circumstance will the seller be liable for any loss, damage, expense or incidental or consequential damage of any kind arising in connection with the use or inability to use its product. Specific conditions of sale and Chase's limited warranty are set out in detail in Chase Corporation Terms and Conditions of Sale. Those Terms and Conditions are the only source that contain Chase's limited warranty and other terms and conditions.