

Advanced Materials

Araldite[®] CY 9729 / Aradur[®] HT 907 / Accelerator DY 9741 Casting System

CYCLOALIPHATIC LIQUID EPOXY REISN CASTING SYSTEM

GENERAL :

A low viscosity, unfilled, casting system exhibiting superior mechanical and electrical properties to meet the most demanding indoor and outdoor applications. This system can be processed by Automatic Pressure Gelation (APG), Pressure Gelation (PG) or Conventional Casting.

FEATURES :

- Greater toughness than porcelain and equal, or superior, to competitive epoxies.
- Better thermal shock resistance.
- Improved weatherability compared to aromatic bisphenol-A epoxies.
- Low dielectric loss and excellent tracking resistance for applications > 105 °C
- Greater toughness and far closer dimensional tolerances result in greater reliability

APPLICATION :

- High voltage circuit breaker bushings
- SF₆ inner frusta
- Air transformer bushings
- Oil transformer bushings
- Stand-off insulators
- Weather sheds on suspension and dead end insulators
- Arc shields
- Station and line post insulators
- Surge arrester castings
- Phase separators
- Structural switchgear parts

TYPICAL PROPERTIES* :**Araldite® CY 9729**

Appearance	Clear to cloudy liquid
Specific gravity	1.115 – 1.145
Viscosity, cPs @ 25 °C	300 – 500
Weight per epoxide	181 – 193
Flash point, Closed Cup, °C	188

Aradur® HT 907

Appearance	Clear to cloudy liquid
Specific gravity	1.15 – 1.20
Viscosity, cPs @ 40 °C	< 100
Melting point, °C	34 – 38
Flash point, Closed Cup, °C	138

Accelerator DY 9741

Appearance	Clear light amber liquid
Specific gravity	1.00 – 1.15
Viscosity, cPs @ 25 °C	30 - 150
Flash point, Closed Cup, °C	111

Mixed Araldite® System

Specific gravity	1.90 – 1.95
Viscosity, cPs @ 25 °C	25,000 – 30,000

* Typical properties are based on Huntsman's test methods. Copies are available upon request.

PACKAGING & STORAGE :**Araldite® CY 9729**

Store at 18 – 25 °C in dry well sealed condition ; if possible, in its original container. If only partly used, be sure to re-close container properly.

Aradur® HT 907

Store 70 – 90 °C. This product is moisture sensitive and packaged under a blanket of dry nitrogen. Maintain seal, after use re-blanket with dry nitrogen and tightly seal.

Accelerator DY 9741 : Combustible liquid. Do not cure or weld container.

Keep away fro heat, sparks, and open flame. Use with adequate ventilation. In case of fire, use CO₂, dry chemical or foam. Stored in sealed containers. Keep containers closed to prevent moisture absorption and contamination.

Under these conditions their shelf lives will be one year from date of shipping. Contact Customer Service for packaging information.

MIX RARIOS :

	Parts by weight
Aradur® HT 907	100
Accelerator DY 9741	74
	2 - 4

PROCESSING DATA :

Mixed viscosity @ 25 °C, cPs	50,000 – 70,000
min @ 120 °C	29 – 35
Recommended cure time, hours	
@ 80 °C	5 +
@ 140 °C	10

PROCESSING AND CURE :

Processing is best accomplished using Automatic Pressure Gelation (APG) Process. Moldings can be produced using Araldite® products with either a one-component or a two-component system. In the one-component process the resin and hardener with accelerator are each separately heated to 50 – 70 °C and blended with filler. The mixer resin and hardener have a pot life of 90 – 120 minutes at 70 °C, as determined by a maximum viscosity of 20,000 cPs. At lower pot temperatures, longer pot lives are obtained.

In the two-component Araldite® system, the resin and hardener components are handled in the same manner as in the one-component system, except that they are mixed in an in-line static mixer immediately prior into the mold. Thus, the resin and hardener are separately heated, mixed with filler and degassed. At this stage, the two components are stable indefinitely (one month or more) with two exceptions : 1) agitation should continue to keep the filler from setting, and 2) water should not be allowed to contaminate either side. If agitation is stopped for more than one day, the filler may settle out and be difficult to redisperse. Tests have shown that addition of 1% water to a mixture of Araldite® products will substantially reduce the heat distortion temperature of a molded part and degrade its dielectric loss properties. Significant advantages of a two-component system include 1) ease of clean up and 2) the ability to stop molding and resume later, even after an overnight break.

The cure cycle for parts depends on the size of the part, the mold temperature and the molding equipment's ability to supply heat to the resin. With the recommended 150 °C mold temperature, for a two-inch diameter part in a steel mold, in-mold time will be about 9 minutes. Smaller parts or high mold temperature will result in shorter cycles. Larger parts or lower mold temperatures will increase cycle times. An in-mold time of 13 minutes is expected for parts with a 4-inch diameter and 17 minutes is expected for parts with a 7-inch diameter at a mold temperature of 150 °C.

All parts should be post-cured soon after removal from the mold. A post cure cycle of 4 hours at 160 °C is recommended, although shorter periods may be satisfactory for smaller parts.

MECHANICAL AND PHYSICAL PROPERTIES :**Note :**

The mechanical properties of this system, when molded, compare favorably with those of competing epoxy insulating materials and porcelain. (All moldings 60 % by weight filled with oven-dried silica.)

Property	Araldite® System	Bis-A Based Epoxy	Porcelain
Tensile strength, psi	8,100	9,000	6,000
Elongation, %	1.0	0.8	0.01
Heat distortion temperature, °C	137	123	800
Tensile modulus, psi	1.3 x 10 ⁶	1.7 x 10 ⁶	8.0 x 10 ⁶
Thermal shock rating	8.4	8.5	Low
Izod toughness, ft-lbs/in	2.5	1.6	0.1

a) Tested with a steel washer cast in resin and alternatively subjected to heat and cooling cycles that increase by 20 °C and decrease by 10 °C each cycle after starting at 60 °C and 20 °C respectively.

b) Un-notched sample, 1/8 inch(3.2 mm) wide, ½ inch (12.8 mm) thick.

This cured Araldite® system possesses higher heat distortion temperatures and also offers excellent toughness and resistance to thermal shock. The tensile strength and modulus are lower at 60 % filler loading, but higher stiffness can readily be attained by increased filler levels. This is easily accomplished due to the lower viscosity of this Araldite® system.

The comparison with porcelain is important. The high heat distortion temperature and modulus-stiffness of porcelain are its well known advantages. In many instances, however, they can result in design "overkill". Porcelain's resulting notch sensitivity causes it to have lower tensile strength and poor toughness. Porcelain parts must be constructed larger and heavier than is necessary with epoxies. This means epoxy parts weigh less and are more mechanically reliable.

**ELECTRICAL PROPERTIES :
(Typical values)**

Property	Araldite® System	Bis-A Based Epoxy	Porcelain
Maximum service temp, °C	125	125	145
Dielectric constant			
@ 25 °C, 60 Hz	3.6	3.6	6.3
@ 125 °C, 60 Hz	4.2	4.2	--
@ 145 °C, 60 Hz	--	--	7.0
Power factor, %			
@ 25 °C, 60 Hz	3.7	3.0	1.8
@ 125 °C, 60 Hz	8.9	9.2	--
@ 145 °C, 60 Hz	--	--	20 +
Volume resistivity			
@ 25 °C, 10 ¹³ ohm.cm	410	90	--
@ 125 °C, 10 ¹³ ohm.cm	2.1	1.4	--
Dielectric strength, V/mil			
1/8 inch (3.2 mm) sample	449	463	240
Carbon track resistance			
ASTM D-2303 (minute)	2,000 +	100	--

The main difference between Araldite® CY 9729 and Bisphenol-A type epoxies are carbon track resistance and volume resistivity. The volume resistivity of the Araldite® cycloaliphatic epoxy system when molded is between 2 and 4 times higher than that of the aromatic Bisphenol-A type epoxy.

The greatest difference between the cycloaliphatic and the aromatic epoxy appears in carbon track resistance. In the test at 2.5 Kv, the aromatic epoxy quickly formed a conductive carbon track and failed. The cycloaliphatic-based molding failed about twenty times more slowly by gradual erosion rather than tracking.

Porcelain does not track like organic materials, but its dielectric loss, power factor and dielectric strength are significantly inferior to that of the cured Araldite® resin. Even more detrimental is porcelain's tendency to crack, disintegrate and fail after arc flashovers caused by lighting or salt buildup on an insulator.

HANDLING/SAFETY PRECAUTIONS :**Araldite® CY 9729**

WARNING Causes skin and eye irritation. May cause allergic skin reaction. Avoid contact with eyes, skin, and clothing. Avoid prolonged or repeated contact with skin. Wash thoroughly after handling.

Aradur® HT 907

DANGER Corrosive – causes eye burns and severe skin irritation. Causes respiratory irritation. May cause allergic skin and respiratory reactions. Do not get in eyes, on skin, or on clothing. Avoid breathing vapor or mist. Avoid prolonged or repeated contact with skin. Keep container closed. Use with adequate ventilation. Wash thoroughly after handling.

Accelerator DY 9741

DANGER Combustible. Corrosive – causes skin and eye burns. Harmful if swallowed. May cause allergic skin reaction. Keep away from heat and flame. Do not get in eyes, on skin, or on clothing. Avoid breathing vapor or mist. Keep container closed. Use with adequate ventilation. Wash thoroughly after handling.

Caution To protect against any potential health risks presented by our products, the use of proper personal protective equipment (PPE) is recommended. Eye and skin protection is normally advised. Respiratory protection may be needed if mechanical ventilation is not available or is insufficient to remove vapors. For detailed PPE recommendations and exposure control options consult the product MSDS or a Huntsman EHS representative.

FIRST AID :**In case of contact :**

Eyes : Flush eyes with plenty of water for 15 minutes and get prompt medical attention.

Skin : Wash skin thoroughly with mild soap and water ; remove contaminated clothing before reuse. Discard contaminated shoes and other articles made of leather.

Inhalation : Remove person to fresh air.

Ingestion : **Do not** induce vomiting. Dilute with plenty of water and contact physician immediately. Never give anything to drink to an unconscious person.

IMPORTANT LEGAL NOTICE

Huntsman Advanced Materials warrants only that its products meet the specifications agreed with the user. Typical properties, where stated, are to be considered as representative of current production and should not be treated as specifications.

The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.

WHILE ALL THE INFORMATION AND RECOMMENDATIONS IN THIS PUBLICATION ARE, TO THE BEST OF HUNTSMAN ADVANCED MATERIAL'S KNOWLEDGE, INFORMATION AND BELIEF, ACCURATE AT THE DATE OF PUBLICATION, nothing herein is to be construed as a warranty, whether express or implied, including but without limitation, as to merchantability or fitness for a particular purpose. In all cases, it is the responsibility of the user to determine the applicability of such information and recommendations and the suitability of any product for its own particular purpose.

The behavior of the products referred to in this publication in manufacturing processes and their suitability in any given end-use environment are dependent upon various conditions such as chemical compatibility, temperature, and other variables, which are not known to Huntsman Advanced Materials. It is the responsibility of the user to evaluate the manufacturing circumstances and the final product under actual end-use requirements and to adequately advise and warn purchasers and users thereof.

Products may be toxic and require special precautions in handling. The user should obtain Safety Data Sheets from Huntsman Advanced Materials containing detailed information on toxicity, together with proper shipping, handling and storage procedures, and should comply with all applicable safety and environmental standards.

Hazards, toxicity and behavior of the products may differ when used with other materials and are dependent on manufacturing circumstances or other processes. Such hazards, toxicity and behavior should be determined by the user and made known to handlers, processors and end users.

Except where explicitly agreed otherwise, the sale of products referred to in this publication is subject to the general terms and conditions of sale of Huntsman Advanced Materials LLC or of its affiliated companies including without limitation, Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas Inc., and Huntsman Advanced Materials (Hong Kong) Ltd.

Huntsman Advanced Materials is an international business unit of Huntsman Corporation. Huntsman Advanced Materials trades through Huntsman affiliated companies in different countries including but not

limited to Huntsman Advanced Materials LLC in the USA and Huntsman Advanced Materials (Europe) BVBA in Europe.

Araldite and Aradur are registered trademarks of Huntsman Corporation or an affiliate thereof in one or more, but not all, countries.

Copyright © 2007 Huntsman Corporation or an affiliate thereof. All rights reserved.

Main Offices :

Huntsman Corporation

10003 Woodloch Forest Dr.
The Woodlands
Texas 77380
(281) 719-6000

**Huntsman Advanced Technology
Center**

8600 Gosling Rd.
The Woodlands
Texas 77381
(281) 719-7400
Website :

www.huntsman.com/advanced_materials