

Advanced Materials**ARALDITE® AW 106 Resin
Hardener HV 953U****MULTI-PURPOSE EPOXY ADHESIVE****DESCRIPTION**

ARALDITE AW 106 Resin/Hardener HV 953U epoxy adhesive is a multi-purpose, viscous material that is suitable for bonding a variety of materials, including metal, ceramic, and wood. The electrically insulating adhesive is easy to apply either manually by spatula and stiff brush or mechanically with meter/mix and coating equipment. Araldite AW 106 Resin/Hardener HV 953U epoxy adhesive cures at temperatures from 68°F (20°C) to 356°F (180°C) with no release of volatile constituents.

FEATURES

Metal
Ceramics
Wood
Vulcanized Rubber
Foams
Plastics

ADVANTAGES

Long open time
High shear and peel strength
Easy to apply
Good resistance to static and dynamic loads
Electrically insulating

**TYPICAL
PROPERTIES**

<u>Property</u>	<u>Test Method</u>	<u>Test Values⁽¹⁾</u>	
		<u>Resin</u>	<u>Hardener</u>
Color/appearance	Visual	Creamy viscous liquid	Amber liquid
Specific Gravity	ASTM D-792	1.17	0.92
Viscosity, cP @ 77°F (25°C)	ASTM D-2393	50,000	35,000

**TYPICAL MIXED
PROPERTIES**

<u>Property</u>	<u>Test Method</u>	<u>Test Values⁽¹⁾</u>
Reaction Ratio (by weight)		100R/80H
Reaction Ratio (by volume)		100R/100H
Pot Life, hrs. @ 77°F (25°C), 4 fl. oz. mass	ASTM D-2471	2
Mixed viscosity, cP @ 77°F (25°C)	ASTM D-2393	45,000

¹Tested @ 77°F (25°C)

**RECOMMENDED
CURE SCHEDULES**

<u>Temperature</u>	<u>Handling Strength</u>	<u>Minimum Cure Time</u>
68°F (20°C)	12 hours	15 hours
77°F (25°C)	7 hours	12 hours
104°F (40°C)	2 hours	3 hours
158°F (70°C)	30 minutes	50 minutes
212°F (100°C)	6 minutes	10 minutes
302°F (150°C)	4 minutes	5 minutes

PROCESSING**Application of Adhesive**

The resin/hardener mix is applied with a spatula to the pretreated and dry joint surfaces.

A layer of adhesive 0.002 to 0.004-inches (0.05 to 0.10-mm) thick will normally impart the greatest lap shear strength to a joint.

The joint components should be assembled and clamped as soon as the adhesive has been applied. Even contact throughout suffices to ensure proper cure.

Standard Test Specimens

Unless otherwise stated, the figures given below were all determined by testing standard specimens made up by lap-jointing 4-inch x 1-inch x 0.06-inch (10-cm x 2.5-cm x 1.5-mm) strips of aluminum. The joint area was 0.5 x 1 inch (12.5 mm x 2.5 cm) in each case.

TYPICAL PHYSICAL PROPERTIES

Lap Shear Strength, psi (MPa)		Test Method
Effect of Cure Time and Test Temperature		ASTM D-1002
Load applied 10 minutes after specimens reach test temperature.		
Cure Temperature	Test Time	Test Values⁽¹⁾
77°F (25°C)	8 hours	710(4.9)
	15 hours	1990(13.7)
	24 hours	2130(14.7)
	72 hours	2280(15.7)
	5 days	2560(17.6)
	1 hour	3130(21.5)
158°F(70°C)	2 hours	3410(23.5)
	3 hours	3200 (22)
	10 minutes	3700 (25.5)
212°F(100°C)	20 minutes	3980 (27.4)
	30 minutes	4120(28.4)
302°F(150°C)	5 minutes	4270 (29.4)
	10 minutes	4410(30.4)
	20 minutes	4410(30.4)

¹Tested @ 77°F (25°C)

Lap Shear Strength, psi (MPa)		Test Method
Effect of Test Temperature		ASTM D-1002
Load applied 10 minutes after specimens reach test temperature.		
Cure Cycle	Test Temp.	Test Values⁽¹⁾
5 days @ 77°F (25°C)	-76°F (60°C)	2840(19.5)
	-4°F (-20°C)	2840(19.5)
	68°F (20°C)	2560(17.6)
	104°F(40°C)	1420(9.8)
	140°F(60°C)	570 (3.9)
	20 min. @ 212°F(100°C)	-76°F (-60°C)
-46°F (-20°C)		3410(23.5)
68°F (20°C)		3980 (27.4)
104°F(40°C)		1990(13.7)
140°F(60°C)		1000 (6.9)

¹Tested @ 77°F (25°C)

Lap Shear Strength, psi (MPa)**Test Method**

ASTM D-1002

Effect of Immersion

Cure cycle 16 hours @ 104°F (40°C). Immersion for 90 days in media listed.

Properties**Test Values⁽¹⁾**

Standard - As prepared	2560(17.6)
Acetone (30 days)	570 (3.9)
Acetylene	430 (2.9)
Gasoline	2410 (16.6)
Ethyl Acetate (30 days)	570 (3.9)
Acetic Acid 10%	Degraded
Methanol	Degraded
Lubricating Oil - HD30	2560(17.6)
Kerosene	Degraded
Trichloroethylene	Degraded
Water @ 68°F (20°C)	1420(9.8)
Water @ 194°F (90°C)	430 (2.9)

Lap Shear Strength, psi (MPa)***Effect of Tropical Exposure***

(104°F/40°C/92% R.H.)

Cure Cycle**Exposure Time****Test Values⁽¹⁾**

16 hrs. @ 104°F (40°C)	0 days	2560(17.6)
	10 days	2560 (17.6)
	30 days	1710(11.8)
	60 days	1560(10.7)
	90 days	570 (3.9)
20 min. @ 212°F (100°C)	0 days	3980 (27.4)
	10 days	2560(17.6)
	30 days	1710(11.8)
	60 days	1560(10.7)
	90 days	1280 (8.8)

¹Tested @ 77°F (25°C)

Lap Shear Strength, psi (MPa)***Effect of Heat Aging***

Cured 16 hours @ 77°F (25°C)

<u>Aging Temperature</u>	<u>Exposure Time</u>	<u>Test Values</u>
68°F (20°C)	0 days	2560(17.6)
	1 years	2560(17.6)
	2 years	2280(15.7)
	3 years	1710(11.8)
	4 years	1990(13.7)
140°F (60°C)	3 days	2560(17.6)
	10 days	2420(16.6)
176°F (80°C)	3 days	2130(14.7)
	10 days	2130(14.7)
	30 days	2130(14.7)
	60 days	2130(14.7)
	1 year	1280(8.8)
	2 years	710(4.9)
	3 years	710(4.9)
	4 years	430 (2.9)
248°F (120°C)	3 days	2130(14.7)
	10 days	2280(15.7)
	30 days	2280(15.7)
	60 days	2130(14.7)

Lap Shear Strength, psi (MPa)***Tested on Metal Substrates***

Cured 20 min @ 77°F (25°C)

<u>Metal</u>	<u>Substrate Thickness (in./mm)</u>	<u>Test Values</u>
Carbon Steel	0.039/1.0	3840 (26.4)
Stainless Steel	0.039/1.0	3270 (22.5)
Galvanized Steel2	0.06/1.5	1990(13.7)
Copper	0.06/1.5	3270 (22.5)
Brass	0.06/1.5	2990 (20.6)

¹Tested @ 77°F (25°C)²Surface degreased only, not roughened.

Fatigue Strength

Tested using a load frequency of 90 Hz and a
1-in. (25 mm) joint overlap
(Cured 20 min. @ 212°F/100°C)

Test Method

ASTM D-1002

**Fatigue Limit Load,
% Static Shear Strength**

50
40
30
25
20
15

Cycles to Failure

$10^3 - 10^4$
 $10^4 - 10^5$
 $10^5 - 10^6$
 $10^5 - 10^6$
 $10^6 - 10^7$
 $>10^7$

PHYSICAL PROPERTIES

	Test Values	Test Method
Ultimate Tensile Strength, psi (MPa)	4,800 (33)	ASTM D-638
Elongation, %	9	ASTM D-638
Tg per DMA, °F (°C)	146 (63)	ASTM D-4065
Hardness, Shore D	80	ASTM D-2240
Coefficient of Thermal Expansion, in./in./°C	8.5×10^{-5}	ASTM E-831
Roller Peel, pli (N/mm)	28 (4.9)	ISO 4578

DIELECTRIC PROPERTIES

	Test Values
Thermal Conductivity, W/mK	0.22
Surface Resistivity, ohms	1.2×10^{16}
Dielectric Strength, V/ml	400
Volume Resistivity, Ω cm	7.1×10^{14}
Dielectric Constant, @ 50Hz/1KHz/10KHz	3.4/3.2/3.2
Loss Tangent, % @ 50Hz/1KHz/10KHz	1.7/1.8/2.6

STORAGE AND SHELF LIFE

ARALDITE epoxy adhesive components should be stored in their original, sealed containers at room temperature. When stored at temperatures from 59-77°F (15-25°C), the resin and hardener will remain in useable condition for 12 months from date of shipping from Huntsman.

**SAFETY/HANDLING
PRECAUTIONS**

Do not use or handle this product until the Material Safety Data Sheet has been read and understood

Personal Hygiene*Safety precautions at workplace*

Protective clothing	Yes
Gloves	Essential
Arm protectors	Recommended when skin contact is likely
Goggles/safety glasses	Yes

Skin protection

Before starting work	Apply barrier cream to exposed skin
After washing	Apply barrier or nourishing cream

Cleansing of contaminated skin

Dab off with absorbent paper, wash with warm water and alkali-free soap, then dry with disposable towels. Do not use solvents.

Clean shop requirements

Cover workbenches/areas with light colored paper. Use disposable beakers.

Disposal of spillage

Soak up with sawdust or cotton waste cloth and deposit in plastic-lined bin.

Ventilation

Of workshop	Renew air 3 to 5 times an hour
Of workplaces	Exhaust fans should be used to prevent operators from inhaling vapors.

FIRST AID

Contamination of the eyes by resin, hardener or mix should be treated immediately by flushing with clean, running water for 10 to 15 minutes. A doctor should then be consulted.

Material smeared or splashed on the *skin* should be dabbed off, and the contaminated area then washed and treated with a cleansing cream (see above). A doctor should be consulted in the event of severe irritation or burns. Contaminated clothing should be changed immediately.

Anyone taken ill after inhaling vapors should be moved out of doors immediately.

In all cases of doubt call for medical assistance.

CAUTION:

Huntsman Advanced Materials Americas Inc. maintains up-to-date Material Safety Data Sheets (MSDS) on all of its products. These sheets contain pertinent information that you may need to protect your employees and customers against any known health or safety hazards associated with our products. Users should review the latest MSDS to determine possible health hazards and appropriate precautions to implement prior to using this material. Copies of the latest MSDS may be requested by calling our customer service group at 888-564-9318 or emailing your request to adhesives@huntsman.com.

**KEEP OUT OF REACH OF CHILDREN
FOR PROFESSIONAL AND INDUSTRIAL USE ONLY**

IMPORTANT LEGAL NOTICE

Sales of the product described herein ("Product") are subject to the general terms and conditions of sale of either Huntsman Advanced Materials LLC, or its appropriate affiliate including without limitation Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas Inc., or Huntsman Advanced Materials (Hong Kong) Ltd. ("Huntsman"). The following supercedes Buyer's documents.

Huntsman warrants that at the time and place of delivery all Products sold to Buyer shall conform to the specifications provided to Buyer by Huntsman.

While the information and recommendations included in this publication are, to the best of Huntsman's knowledge, accurate as of the date of publication, NOTHING CONTAINED HEREIN (EXCEPT AS SET FORTH ABOVE REGARDING CONFORMANCE WITH SPECIFICATIONS PROVIDED TO BUYER BY HUNTSMAN) IS TO BE CONSTRUED AS A REPRESENTATION OR WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, NONINFRINGEMENT OF ANY INTELLECTUAL PROPERTY RIGHTS, OR WARRANTIES AS TO QUALITY OR CORRESPONDENCE WITH PRIOR DESCRIPTION OR SAMPLE, AND THE BUYER ASSUMES ALL RISK AND LIABILITY WHATSOEVER RESULTING FROM THE USE OF SUCH PRODUCT, WHETHER USED SINGLY OR IN COMBINATION WITH OTHER SUBSTANCES.

No statements or recommendations made herein are to be construed as a representation about the suitability of any Product for the particular application of Buyer or user or as an inducement to infringe any patent or other intellectual property right. Buyer is responsible to determine the applicability of such information and recommendations and the suitability of any Product for its own particular purpose, and to ensure that its intended use of the Product does not infringe any intellectual property rights.

The Product may be or become hazardous. The Buyer should obtain Material Safety Data Sheets and Technical Data Sheets from Huntsman containing detailed information on Product hazards and toxicity, together with proper shipping, handling and storage procedures for the Product, and should comply with all applicable governmental laws, regulations and standards relating to the handling, use, storage, distribution and disposal of, and exposure to the Product. Buyer shall also take all steps necessary to adequately inform, warn and familiarize its employees, agents, direct and indirect customers and contractors who may handle or be exposed to the Product of all hazards pertaining to and proper procedures for safe handling, use, storage, transportation and disposal of and exposure to the Product, and the containers or equipment in which the Product may be handled, shipped or stored.

Araldite is a registered trademark of Huntsman Corporation or an affiliate thereof in one or more, but not all countries.

© 2007 Huntsman Advanced Materials Americas Inc.

Main Offices :

Huntsman Corporation
10003 Woodloch Forest Dr.
The Woodlands
Texas 77380
(281) 719-6000

Huntsman Advanced Technology Center

8600 Gosling Rd.
The Woodlands
Texas 77381
(281) 719-7400