

## Advanced Materials

# Arathane<sup>®</sup> AW 5540 Resin Hardener HW 5541 or Hardener HW 5542 Adhesive

### POLYURETHANE ADHESIVE

- Varied work lives
- Sag resistance
- Flexible

---

### DESCRIPTION :

Arathane<sup>®</sup> AW 5540 Resin with Hardener HW 5541 or Hardener HW 5542 polyurethane adhesive is a versatile system designed for use with automatic mixing and dispensing equipment. Arathane<sup>®</sup> AW 5540 Resin with Hardener HW 5541 polyurethane adhesive produces a work life of 10 to 15 minutes. Arathane<sup>®</sup> AW 5540 Resin with Hardener HW 5542 polyurethane adhesive has a 2 to 3-minute work life. Once cured, the adhesives exhibit identical physical properties and are well suited for use on SMC, fiberglass-reinforced plastics, cured plastics and metals.

---

### APPLICATIONS :

- SMC
- Fiberglass-reinforced plastics
- Cured plastics
- Metal

---

### ADVANTAGES :

- 1:1 mix ratio by volume
- Easy to pump
- Color coded
- Thixotropic and non sagging (1/4-in. (6mm) bead
- Excellent adhesion
- Fast curing
- Good moisture resistance
- Formulated without asbestos, MOCA (44' methylene bis [2-chloroaniline]), or TDI (toluene diisocyanate)

---

**TYPICAL PROPERTIES :**

<u>Property</u>	<u>Test Method</u>	<u>Test Values<sup>(1)</sup></u>	
		<u>Resin</u>	<u>Hardener</u>
Color/Appearance	Visual	Dark Brown liquid	Red liquid
Specific Gravity @ 73 °F (25 °C)	ASTM D-792	1.4	1.3
Viscosity (cP) @ 77 °F (25 °C)	ASTM D-2393	60,000	20,000

---

**TYPICAL MIXED PROPERTIES :**

<u>Property</u>	<u>Test Method</u>	<u>Test Values<sup>(1)</sup></u>
Color	Visual	Dark Red
Reaction Ratio (by weight)		100R/95H
Reaction Ratio (by volume)		100R/100H
Sag Resistance, in (mm), Horizontal, Vertical		1/4 (6) 1/8 (3)
Pot Life, minutes @ 77 °F (25 °C), With HW 5541 With HW 5542	ASTM D-2471	15 3

<sup>(1)</sup> Tested @ 77 °F (25 °C)

---

**RECOMMENDED CURE SCHEDULES :**

<u>Temperature</u>	<u>Minimum Cure Time</u>	
	<u>AW 5540 / HW 5541 System</u>	<u>AW 5540 / HW 5542 System</u>
68 °F (20 °C)	16 hours	6 hours
140 °F (60 °C)	2 hours	1 hour
212 °F (100 °C)	10 minutes	10 minutes



**Property****Lap Shear Strength vs. Time****Arathane® AW 5540 Resin/Hardener HW 5541 polyurethane adhesive**

At 77 °F (25 °C), psi (MPa)

Substrate : Alclad 2024 T-3 Aluminum, Etched per ASTM D-2651 (Methode A)

Bond line Overlap : 0.5 in. (12.5 mm)

Bond line Thickness : 0.030 in (0.8 mm)

<b><u>Time</u></b>	<b><u>Strength</u></b>
2 hours	14 (0.1)
4 hours	103 (0.7)
8 hours	146 (1)
24 hours (1 day)	1,035 (7.1)
48 hours (2 days)	1,266 (8.7)
120 hours (5 days)	1,286 (8.7)
168 hours (7 days)	1,300 (9)
240 hours (10 days)	1,338 (9.2)
336 hours (14 days)	1,312 (9)

**Property****Lap Shear Strength vs. Time****Arathane® AW 5540 Resin/Hardener HW 5542 polyurethane adhesive**

At 77 °F (25 °C), psi (MPa)

Substrate : Elpo Coated Steel

Bond line Overlap : 0.5 in. (12.5 mm)

Bond line Thickness : 0.030 in (0.8 mm)

<b><u>Time</u></b>	<b><u>Strength</u></b>
2 hours	320 (2.2)
4 hours	879 (6)
8 hours	894 (6.2)
24 hours (1 day)	1,820 (12.5)
48 hours (2 days)	1,347 (9.3)
72 hours (3 days)	1,466 (10.1)
168 hours (7 days)	1,424 (9.8)

**Property**

Elongation at break, %  
Tensile Strength @ 77 °F (25 °C), psi (MPa)  
Hardness (Shore D)

**Test Method**

ASTM D-638  
ASTM D-638  
ASTM D-2240

**Test Values<sup>(1)</sup>**

80  
2,500 (17.2)  
65

<sup>(1)</sup> Tested @ 77 °F (25 °C)

---

**CAUTION :**

Huntsman Advances Materials Americas Inc. maintains up-to-date Material Safety Data Sheet (MSDS) on all of its products. These sheets contain pertinent information that you may need to protect your employees and customers against any known health or safety hazards associated with our products. Users should review the latest MSDS to determine possible health hazards and appropriate precautions to implement prior to using this material. Copies of the latest MSDS may be requested by calling our customer service group at 800-367-8793 or emailing your request to [adhesives\\_group@huntsman.com](mailto:adhesives_group@huntsman.com)

To protect against any potential health risks presented by our products, the use of proper personal protective equipment (PPE) is recommended. Eye and skin protection is normally advised. Respiratory protection may be needed if mechanical ventilation is not available or is insufficient to remove vapors. For detailed PPE recommendations and exposure control options consult the product MSDS or a Huntsman EHS representative.

---

**FIRST AID :**

Eyes and skin : Flush eyes with water for 15 minutes. Contact a physician if irritation persists. Wash skin thoroughly with soap and water. Remove and wash contaminated clothing before reuse.

Inhalation : Remove subject to fresh air.

Swallowing : Dilute by giving water to drink and contact a physician promptly. Never give anything to drink to an unconscious person.

**KEEP OUT OF REACH OF CHILDREN****FOR PROFESSIONAL AND INDUSTRIAL USE ONLY**

---

**IMPORTANT LEGAL NOTICE**

Huntsman Advanced Materials warrants only that its products meet the specifications agreed with the user. Typical properties, where stated, are to be considered as representative of current production and should not be treated as specifications.

The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.

WHILE ALL THE INFORMATION AND RECOMMENDATIONS IN THIS PUBLICATION ARE, TO THE BEST OF HUNTSMAN ADVANCED MATERIAL'S KNOWLEDGE, INFORMATION AND BELIEF, ACCURATE AT THE DATE OF PUBLICATION, nothing herein is to be construed as a warranty, whether express or implied, including but without limitation, as to merchantability or fitness for a particular purpose. In all cases, it is the responsibility of the user to determine the applicability of such information and recommendations and the suitability of any product for its own particular purpose.

The behavior of the products referred to in this publication in manufacturing processes and their suitability in any given end-use environment are dependent upon various conditions such as chemical compatibility,

temperature, and other variables, which are not known to Huntsman Advanced Materials. It is the responsibility of the user to evaluate the manufacturing circumstances and the final product under actual end-use requirements and to adequately advise and warn purchasers and users thereof.

Products may be toxic and require special precautions in handling. The user should obtain Safety Data Sheets from Huntsman Advanced Materials containing detailed information on toxicity, together with proper shipping, handling and storage procedures, and should comply with all applicable safety and environmental standards.

Hazards, toxicity and behavior of the products may differ when used with other materials and are dependent on manufacturing circumstances or other processes. Such hazards, toxicity and behavior should be determined by the user and made known to handlers, processors and end users.

Except where explicitly agreed otherwise, the sale of products referred to in this publication is subject to the general terms and conditions of sale of Huntsman Advanced Materials LLC or of its affiliated companies including without limitation, Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas Inc., and Huntsman Advanced Materials (Hong Kong) Ltd.

Huntsman Advanced Materials is an international business unit of Huntsman Corporation. Huntsman Advanced Materials trades through Huntsman affiliated companies in different countries including but not limited to Huntsman Advanced Materials LLC in the USA and Huntsman Advanced Materials (Europe) BVBA in Europe.

Arathane is a registered trademark of Huntsman Corporation or an affiliate thereof in one or more, but not all, countries.

Copyright © 2007 Huntsman Corporation or an affiliate thereof. All rights reserved.

Main Offices :

**Huntsman Corporation**  
10003 Woodloch Forest Dr.  
The Woodlands  
Texas 77380  
(281) 719-6000

**Huntsman Advanced Technology  
Center**

8600 Gosling Rd.  
The Woodlands  
Texas 77381  
(281) 719-7400  
Website :

[www.huntsman.com/advanced\\_materials](http://www.huntsman.com/advanced_materials)