

Advanced Materials**RenCast[®] 4036 / Ren[®] 1500 Casting System****HEAT RESISTANT CASTING SYSTEM****DESCRIPTION :**

RenCast[®] 4036 (Resin) can be used with Ren[®] 1500 (Hardener) to provide an aluminum-filled casting system intended for continual use to 300 °F (149 °C). Intermittent use to 350 °F (177 °C) is possible. RenCast[®] 4036 casting system can be cast to 2.5 cm (1") thick in nonconductive molds when used with Ren[®] 1500 Hardener. Bulk fillers such as Ren[®] RP 38 and RP 39 aluminum grain or RP 37 aluminum "puffs" can be added to the RP 4036 system to reduce shrinkage and exotherm while reducing the total tool cost.

APPLICATIONS :

- Vacuum form molds
- Compression and injection molds
- Tools used at elevated temperatures up to 300 °F

MIXING INTRUSCTIONS :

Reaction Ratio 100R to 6H by weight
 100R to 10H by volume

Mixing: Stir each component thoroughly before use. Weigh each component accurately (\pm 5%) into clean containers. Thoroughly mix resin and hardener together (minimum 3 minutes) scraping container sidewalls, bottom and mixing stick several times to assure a uniform mix.

TYPICAL MIXED PROPERTIES :

Property	ASTM Test Method	Test Values⁽¹⁾
Gel Time (4 fl. oz.)	D-2471	60 min.
Color Resin	Visual	Gray
Hardener		Amber
Mixed		Gray
Viscosity, mixed	D-2393	20,000 cP

⁽¹⁾ Tested @ 77 °F (25 °C)

TYPICAL CURED PROPERTIES :

Property	ASTM Test Method	Test Values⁽¹⁾
Specific Gravity (cast)	D-792	1.69
Cubic inch per pound	D-792	16.5
Hardness (Shore D)	D-2240	90
Ultimate Compressive Strength (psi)	D-695	
@ 77 °F		30,000
@ 250 °F		21,000
@ 300 °F		18,000
@ 350 °F		13,000
Ultimate Flexural Strength (psi)	D-790	7,500
Flexural Modulus (psi)	D-790	1.0 x 10 ⁶
Ultimate Tensile Strength (psi)	D-638	6,500
Tg per DMA (°F)	D-4065	350
Coefficient of Thermal Expansion (in/in/°F)	D-3386	1.90 x 10 ⁻⁵
Shrinkage (in/in)	ERF Mold #1	0.0044

⁽¹⁾ Cure Schedule – 24 hrs. at RT, 2 hrs. at 150 °F (66 °C) + 2 hrs. at 200 °F (93 °C) + 2 hrs. at 250 °F (121 °C) + 2 hrs. at 300 °F (149 °C), tested @ 77 °F unless otherwise stated.

NOTE : Typical Properties – These physical properties are reported as typical test values obtained by our test laboratory. If assistance is needed establishing product specifications, please consult with our Quality Control Department.

CURING INSTRUCTIONS :

After gelling at room temperature, the following post cure schedule is recommended : two hours at 15 °F (66 °C), plus two hours at 200 °F (93 °C), plus two hours at 250 °F (121 °C), plus two hours at 300 °F (149 °C).

Temperature limitations of the mold or model dictate whether it can be used as the supporting structure during the post cure cycle. If the tool must be pulled from the mold for the post cure, a supporting frame must be provided.

STORAGE/HANDLING INFORMATION :**RenCast[®] 4036 / Ren[®] 1500**

Store at 60 - 100 °F in a dry place. After use tightly reseal.

Work in a well ventilated area and use clean, dry tools for mixing and applying. For two component system, combine the resin and hardener according to mix ration. Mix together thoroughly and use immediately after mixing. Material temperature should not be below 65 °F (18 °C) when mixing.

RenCast® 4036

This product may crystallize upon storage. If crystallized, vent container and heat to 125 – 145 °F until crystals dissolve. Stir well after product has liquefied.

Stir well before use. This material will separate.

SHELF LIFE :

Provided materials are stored under the recommended storage conditions in their original containers, they will remain in useable condition for at least one year from date of shipping.

PACKAGING :

This product is available in the following package size(s) :

Small Preweighed Units : 6 quart resin / 6 preweighed hardener

Pail Units : Pail resin with appropriate hardener

Please call Customer Service (800-367-8793) for price and availability.

SAFETY/HANDLING PRECAUTIONS :

Do not use or handle this product until the Material Safety Data Sheet has been read and understood.

RenCast® 4036

DANGER. Causes severe skin irritation. Causes eye irritation. May cause skin burns and allergic skin reaction. Avoid contact with eye, skin, or clothing. Avoid prolonged or repeated contact with skin. Wash thoroughly after handling.

Ren® 1500

DANGER CORROSIVE – Causes skin and eye burns. Harmful if absorbed through skin. May cause allergic skin and respiratory reactions.

Do not get in eyes, on skin, or on clothing. Avoid breathing vapor or mist. Keep container closed. Use with adequate ventilation. Wash thoroughly after handling.

Nuisance dust may be generated when sanding or sawing cured material.

FIRST AID :

In case of contact with :

Skin : Immediately wash with soap and water. Remove contaminated clothing and launder before reuse. Destroy contaminated shoes.

Eyes : Immediately flush with water for at least 15 minutes. Call a physician.

Ingestion : If conscious, give plenty of water to drink. Do not induce vomiting. Call a physician.

Inhalation : Remove to fresh air. Administer oxygen or artificial respiration if necessary. Call a physician.

Other : Referral to physician is recommended if there is any question about the seriousness of any injury.

PRECAUTION NOTE :

Thermosetting systems generate heat when curing. The amount of heat and the period of time in which heat is released vary significantly between systems. Additionally, ambient or compound temperature, amount of material mixed, and construction and shape of the mold or container can also be factors in the temperature profile of a mixed system. In some cases, the thermosetting reaction can be vigorous, generation heat sufficient to cause decomposition of the system with subsequent liberation of large volumes of acrid smoke.

A good rule of thumb is never mix more material than can be applied during the stated pot life or gel time. Also take care when using materials in applications other than stated on the product Data Sheet, i.e., a laminating resin for casting.

Please feel welcome to call our Product Information Department or your local Ren representative for instructions before you start your job.

Caution To protect against any potential health risks presented by our products, the use of proper personal protective equipment (PPE) is recommended. Eye and skin protection is normally advised.

Respiratory protection may be needed if mechanical ventilation is not available or is insufficient to remove vapors. For detailed PPE recommendations and exposure control options consult the product MSDS or a Huntsman EHS representative.

IMPORTANT LEGAL NOTICE

Huntsman Advanced Materials warrants only that its products meet the specifications agreed with the user. Typical properties, where stated, are to be considered as representative of current production and should not be treated as specifications.

The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.

WHILE ALL THE INFORMATION AND RECOMMENDATIONS IN THIS PUBLICATION ARE, TO THE BEST OF HUNTSMAN ADVANCED MATERIAL'S KNOWLEDGE, INFORMATION AND BELIEF, ACCURATE AT THE DATE OF PUBLICATION, nothing herein is to be construed as a warranty, whether express or implied, including but without limitation, as to merchantability or fitness for a particular purpose. In all cases, it is the responsibility of the user to determine the applicability of such information and recommendations and the suitability of any product for its own particular purpose.

The behavior of the products referred to in this publication in manufacturing processes and their suitability in any given end-use environment are dependent upon various conditions such as chemical compatibility, temperature, and other variables, which are not known to Huntsman Advanced Materials. It is the responsibility of the user to evaluate the manufacturing circumstances and the final product under actual end-use requirements and to adequately advise and warn purchasers and users thereof.

Products may be toxic and require special precautions in handling. The user should obtain Safety Data Sheets from Huntsman Advanced Materials containing detailed information on toxicity, together with proper shipping, handling and storage procedures, and should comply with all applicable safety and environmental standards.

Hazards, toxicity and behavior of the products may differ when used with other materials and are dependent on manufacturing circumstances or other processes. Such hazards, toxicity and behavior should be determined by the user and made known to handlers, processors and end users.

Except where explicitly agreed otherwise, the sale of products referred to in this publication is subject to the general terms and conditions of sale of Huntsman Advanced Materials LLC or of its affiliated companies including without limitation, Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas Inc., and Huntsman Advanced Materials (Hong Kong) Ltd. Huntsman Advanced Materials is an international business unit of Huntsman Corporation. Huntsman Advanced Materials trades through Huntsman affiliated companies in different countries including but not limited to Huntsman Advanced Materials LLC in the USA and Huntsman Advanced Materials (Europe) BVBA in Europe.

Ren and Rencast are registered trademarks of Huntsman Corporation or an affiliate thereof in one or more, but not all, countries.

Copyright © 2007 Huntsman Corporation or an affiliate thereof. All rights reserved.

Main Offices :

Huntsman Corporation
10003 Woodloch Forest Dr.
The Woodlands
Texas 77380
(281) 719-6000

**Huntsman Advanced Technology
Center**

8600 Gosling Rd.
The Woodlands
Texas 77381
(281) 719-7400

Website :

www.huntsman.com/advanced_materials