

Advanced Materials**RenCast[®] 6498 System / Ren[®] 6498 System**

FLEXIBLE POLYURETHANE SYSTEM

DESCRIPTION :

RenCast[®] 6498 System /Ren[®] 6498 System, a non-mercury, flexible polyurethane system. This product is a new development in the family of RenCast[®] fast polyurethanes, which have been specially formulated to have an interesting combination of long work time (gel time) and short demolding time.

RenCast[®] 6498 System is designed to produce rubber-like parts with flexibility and hardness of 80-90 Shore A.

APPLICATIONS :

- Handcasting
- Vacuum Casting
- Pressure Pot Casting

ADVANTAGES :

- Contains no mercury catalyst
- Convenient mix ratio
- Can be used in a broad range of processes
- Neutral color makes this system pigmentable

MIXING INSTRUCTIONS :

Reaction Ratio 50R to 100H by weight

45R to 100H by volume

TYPICAL MIXED PROPERTIES :

Color	Amber
Reaction Ratio, by weight	50R/100H
Mixed Viscosity, cp	1700 cps @ 2 min
Gel Time 150 gm mass	5 - 6 min
Demold Time (depending upon part thickness and geometry)	2 hours @ RT 0.5 (30 minutes) @ 140F

TYPICAL CURED PROPERTIES :

Cured Color	Amber
Hardness	85 Shore A
Tensile Strength	950 psi
% Elongation at Break	180%
Tear Strength	180 ppi

STORAGE/HANDLING INFORMATION :

Store at 70° - 90°F. This product is moisture sensitive and packaged under a blanket of dry nitrogen. Maintain factory seal. After use reblanket with nitrogen and tightly reseal. This product may crystallize upon storage. If crystallized, vent container and heat to 125° - 145°F until crystals dissolve. Stir well after product has liquefied. If

heating of products in plastic packaging is necessary, heat in a ventilated oven to 145°F maximum. Before heating loosen the container lid slightly to relieve any pressure buildup and place container to be heated into a metal bucket of sufficient volume to contain the product, should the container tip over or leak. Work in a well ventilated area and use clean, dry tools for mixing and applying.

Combine the resin and hardener according to mix ratio, mix together thoroughly and use immediately after mixing. Material temperature should not be below 65°F (18°C) when mixing.

SHELF LIFE :

Provided materials are stored under the recommended storage conditions in their original containers, they will remain in useable condition for at least six months from date of shipping.

PACKAGING :

This product is available in the following package sizes:

Prewriteghed gallon kit (12# total) contains 4# of resin base and 8# of hardener catalyst and 5-gallon pails containing 20# of resin base and 40# of hardener catalyst

Please call Customer Service (800) 367-8793 for price and availability

SAFETY/HANDLING PRECAUTIONS :

Do not use or handle this product until the Material Safety Data Sheet has been read and understood.

FIRST AID :

In case of contact with:

Skin: Immediately wash with soap and water. Remove contaminated clothing and launder before reuse. Destroy contaminated shoes.

Eyes: Immediately flush with water for at least 15 minutes. Call a physician.

Ingestion: If conscious, give 2-4 glasses of water to drink. Do not induce vomiting. Call a physician.

Inhalation: Remove to fresh air. Call a physician.

PRECAUTIONARY NOTE :

Thermosetting systems generate heat when curing. The amount of heat and the period of time in which heat is released vary significantly between systems. Additionally, ambient or compound temperature, amount of material mixed, and construction and shape of the mold or container can also be factors in the temperature profile of a mixed system. In some cases, the thermosetting reaction can be vigorous, generating heat sufficient to cause decomposition of the system with subsequent liberation of large volumes of acrid smoke.

A good rule of thumb is never mix more material than can be applied during the stated pot life or gel time. Also take care when using materials in applications other than stated on the Product Data Sheet, i.e., a laminating resin for casting.

Please feel welcome to call our Product Information Department or your local Ren representative for instructions before you start your job.

Caution

To protect against any potential health risks presented by our products, the use of proper personal protective equipment (PPE) is recommended. Eye and skin protection is normally advised. Respiratory protection may be needed if mechanical ventilation is not available or is insufficient to remove vapors. For detailed PPE recommendations and exposure control options consult the product MSDS or a Huntsman EHS representative.

IMPORTANT LEGAL NOTICE

Huntsman Advanced Materials warrants only that its products meet the specifications agreed with the user. Typical properties, where stated, are to be considered as representative of current production and should not be treated as specifications.

The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.

While all the information and recommendations in this publication are, to the best of Huntsman Advanced Material's knowledge, information and belief, accurate at the date of publication, NOTHING HEREIN IS TO BE CONSTRUED AS A WARRANTY, WHETHER EXPRESS OR IMPLIED, INCLUDING BUT WITHOUT LIMINATION, AS TO MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. IN ALL CASES, IT IS THE RESPONSIBILITY OF THE USER TO DETERMINE THE APPLICABILITY OF SUCH INFORMATION AND RECOMMENDATIONS AND THE SUITABILITY OF ANY PRODUCT FOR ITS OWN PARTICULAR PURPOSE.

The behavior of the products referred to in this publication in manufacturing processes and their suitability in any given end-use environment are dependent upon various conditions such as chemical compatibility, temperature, and other variables, which are not known to Huntsman Advanced Materials. It is the responsibility of the user to evaluate the manufacturing circumstances and the final product under actual end-use requirements and to adequately advise and warn purchasers and users thereof.

Products may be toxic and require special precautions in handling. The user should obtain Safety Data Sheets from Huntsman Advanced Materials containing detailed information on toxicity, together with proper shipping, handling and storage procedures, and should comply with all applicable safety and environmental standards.

Hazards, toxicity and behavior of the products may differ when used with other materials and are dependent on manufacturing circumstances or other processes. Such hazards, toxicity and behavior should be determined by the user and made known to handlers, processors and end users.

Except where explicitly agreed otherwise, the sale of products referred to in this publication is subject to the general terms and conditions of sale of Huntsman Advanced Materials LLC or of its affiliated companies including without limitation, Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas Inc., and Huntsman Advanced Materials (Hong Kong) Ltd.

Huntsman Advanced Materials is an international business unit of Huntsman Corporation. Huntsman Advanced Materials trades through Huntsman affiliated companies in different countries including but not limited to Huntsman Advanced Materials LLC in the USA and Huntsman Advanced Materials (Europe) BVBA in Europe.

RenCast and Ren are registered trademarks of Huntsman Corporation or an affiliate thereof in one or more, but not all, countries.

Copyright © 2007 Huntsman Corporation or an affiliate thereof. All rights reserved.

Main Offices :

Huntsman Corporation
10003 Woodloch Forest Dr.
The Woodlands
Texas 77380
(281) 719-6000

**Huntsman Advanced Technology
Center**

8600 Gosling Rd.
The Woodlands
Texas 77381
(281) 719-7400

Website :

www.huntsman.com/advanced_materials