

# LORD® 7100 and 7150 Urethane Adhesives

## Description

LORD® 7100 and 7150 adhesives are two-part, high strength urethane adhesives used to bond cloth, paper, plastics, foams, rubber, painted metals and powder coated metals. LORD 7100-A and 7150-A resins are composed of isocyanate. LORD 7100-B and 7150-B curatives are composed of polyol.

These adhesives can be either room temperature cured or heat cured for faster processing. LORD 7100 adhesive cures to a glossy black appearance; LORD 7150 adhesive cures to a unique gray color.

## Features and Benefits

**Convenient** – reduces material and labor costs by eliminating the need to prime many plastics.

**Durable** – creates high strength bonds to plastics without crazing, attacking or lowering the strength of the plastic substrate.

**Non-Flammable** – does not require explosion-proof equipment.

**Environmentally Friendly** – no VOC content; does not contain ozone depleting chemicals.

**Chemically Resistant** – solvent resistant when cured.

**Environmentally Resistant** – resists weathering and aging.

## Application

**Surface Preparation** – Surfaces should be free of grease, dirt and other contaminants. For most plastics, clean the surface with a dry rag wipe or a rag dampened with solvent. For metals, grit blast and solvent wash the surface, then prime for optimum bond performance.

**Mixing** – Mix resin with the appropriate curative at a 1:2 ratio, by volume. Handheld cartridges will automatically dispense the correct volumetric ratio of each component. Once mixed, the adhesive cures rapidly.

**Applying** – Apply adhesive using handheld cartridges or automatic meter/mix/dispense equipment.

- Handheld Cartridges
  1. Load the cartridge into the applicator gun and remove the end caps.
  2. Level the plungers by expelling a small amount of adhesive to ensure both sides are level.
  3. Attach mixing tip and expel a mixer's length of adhesive.
  4. Apply adhesive to substrate and mate the parts within the working time of the adhesive. Clamp in position until adhesive reaches handling strength.

## Typical Properties\*

	7100-A Resin	7100-B Curative	7150-A Resin	7150-B Curative
Appearance	Black Liquid	Black Liquid	Black Liquid	White Liquid
Viscosity, cP @ 75°F (24°C)	3000-16,000 Brookfield LVT Spindle 4, 30 rpm	45,000-72,000 Brookfield HA Spindle 6, 20 rpm	3000-16,000 Brookfield LVT Spindle 4, 30 rpm	41,500-65,500 Brookfield HA Spindle 6, 20 rpm
Density				
lb/gal	12.4-12.7	10.9-11.4	12.4-12.7	10.9-11.4
(kg/m <sup>3</sup> )	(1486-1522)	(1306-1366)	(1486-1522)	(1306-1366)
Flash Point (Closed Cup), °F (°C)	>200 (>93)	>200 (>93)	>200 (>93)	>200 (>93)

\*Data is typical and not to be used for specification purposes.

# LORD TECHNICAL DATA

- Meter/Mix/Dispense Equipment  
Contact your LORD representative if assistance is needed using this equipment.

**Curing** – LORD 7100 and 7150 adhesives will cure to full strength in 24 hours at room temperature, 77°F (25°C). Cure rate can be accelerated when adhesive is cured at elevated temperatures.

**Cleanup** – Remove adhesive squeeze-out with a dry knife blade or similar device when the adhesive begins to harden. Take care to avoid disrupting the bondline.

## Shelf Life/Storage

Shelf life is six months when stored at temperatures under 80°F (27°C) in original, unopened container. For maximum shelf life, storage temperatures of 40-50°F

(4-10°C) are recommended. If stored at these cooler temperatures, allow product to return to room temperature before using.

After opening, protect adhesive from excessive exposure to moisture by installing desiccant cartridges and/or using dry nitrogen as an inert cover.

## Cautionary Information

Before using this or any LORD product, refer to the Material Safety Data Sheet (MSDS) and label for safe use and handling instructions.

*For industrial/commercial use only.* Must be applied by trained personnel only. Not to be used in household applications. Not for consumer use.

## Typical Properties\* of Resin Mixed with Curative

	7100-A/B	7150-A/B
Mix Ratio, Resin to Curative		
by Volume	1:2	1:2
by Weight	1:1.78	1:1.78
Solids Content by Weight, %	100	100
Working Time, min @ 77°F (25°C)	5-10	5-10
Purge Time, min @ 77°F (25°C)	3	3
Time to Handling Strength, hr @ 73°F (23°C)	2-3	2-3

\*Data is typical and not to be used for specification purposes.

Values stated in this technical data sheet represent typical values as not all tests are run on each lot of material produced. For formalized product specifications for specific product end uses, contact the Customer Support Center.

Information provided herein is based upon tests believed to be reliable. In as much as LORD Corporation has no control over the manner in which others may use this information, it does not guarantee the results to be obtained. In addition, LORD Corporation does not guarantee the performance of the product or the results obtained from the use of the product or this information where the product has been repackaged by any third party, including but not limited to any product end-user. Nor does the company make any express or implied warranty of merchantability or fitness for a particular purpose concerning the effects or results of such use.

LORD and "Ask Us How" are trademarks of LORD Corporation or one of its subsidiaries.

LORD provides valuable expertise in adhesives and coatings, vibration and motion control, and magnetically responsive technologies. Our people work in collaboration with our customers to help them increase the value of their products. Innovative and responsive in an ever-changing marketplace, we are focused on providing solutions for our customers worldwide . . . Ask Us How.

### LORD Corporation World Headquarters

111 Lord Drive  
Cary, NC 27511-7923  
USA

**Customer Support Center** (in United States & Canada)  
+1 877 ASK LORD (275 5673)

[www.lord.com](http://www.lord.com)