




Wondermask P Temporary Solder Mask 2211

Prevent soldering protected areas in a wave soldering process by applying WonderMASK. Designed to apply smoothly, dry quickly, withstand high leadfree process temperatures, and then be removed easily. Also used for masking conformal coating.



Non-ammoniated, low odor peelable mask

Techspray's original synthetic latex peelable solder mask

- Non-ammoniated
- Non-flammable
- Non-ozone depleting
- Easily peelable
- Low odor
- Cure indicator – darkens as it cures
- Compatible with gold and copper leads
- Non-corrosive
- Non-flammable

Product Packaging

2211-8SQ
Wondermask P
8 oz
24 units/case



2211-G
Wondermask P
1 gal
1 units/case



2211-5G
Wondermask P
5 gal
1 units/case



2211-54G
Wondermask P
54 gal
1 units/case



Instructions

Apply a 20 to 30 mil coating for best results to desired area. The substrate should be free from grease, oil, and particulates. Drying times depend on ambient humidity. Under normal conditions, WonderMASK P is ready for preheating stage in 1 hour, however, cure can be accelerated to 30 minutes at 65°C/150°F or 20 minutes at 82°C/180°F. Do not over cure, as blistering of mask can occur, causing removal problems. Mask will change from an opaque pink to a translucent red when complete cure is accomplished. Mask does not have to be completely cured to withstand soldering operation; however, it should be completely translucent before removal.

Chemical & Physical Properties

Appearance	Pink viscous gel
Odor	Low odor
Flash Point	none
VOC (EPA)	28 g/l
VOC (CARB)	
Boiling Point	
Density	1

Chemical Composition

CHEMICAL NAME	CAS #
Acrylic Latex Polymer	27401-61-2
LECIITHIN	8029-76-3
Alkoxylated alkylphenol	9064-13-5
Tetrakis-[methylene(3,5-di-tert-butyl-4-hydroxyhydrocinnamate)]-methane	6683-19-8
2-Propenoic acid, telomer with 2-methyl-2-[(1-oxo-2-propenyl)amino]-1-propanesulfonic acid monosodium salt and sodium hydrogen sulfite, sodium salt	97953-25-8
C7 - C9 alkyl benzyl phthalate	68515-40-2

Environmental Policy

Techspray is committed to developing products to ensure a safer and cleaner environment. We will continue to meet and sustain the regulations of all federal, state and local government agencies.

Resources

Techspray products are supported by a global sales, technical and customer services resources.

For additional technical information on this product or other Techspray products in the United States, call the technical sales department at 800-858-4043, email tsales@techspray.com or visit our web site at: www.techspray.com.

North America

Techspray
P.O. Box 949
Amarillo, TX 79105
800-858-4043
email: tsales@techspray.com

Europe

ITW Contamination Control BV
Saffierlaan 5
2132 VZ Hoofddorp
The Netherlands
+31 88 1307 400
email: info@itw-cc.com

Countries Outside US

Call to locate a distributor in your country

Important Notice to Purchaser/User: The information in this publication is based on tests that we believe are reliable. The results may vary due to differences in tests type and conditions. We recommend that each user evaluate the product to determine its suitability for the intended application. Conditions of use are outside our control and vary widely. Techspray's only obligation and your only solution is replacement of product that is shown to be defective when you receive it. In no case will Techspray be liable for any special, incidental, or consequential damages based on breach of warranty, negligence or any other theory.